

BURGUNDY



Main Origin / Quarry Location	France
Compression Break. Load:	71,6 MPa
Bending Strength:	8 MPa
Volumetric Weight:	2,01 T/ m3
Apparent Porosity:	18 %
Sonic Speed	3870 m/s
Abrasion Test:	30,9mm